



RUBEROID®

HW PLUS GRANULE MEMBRANE

Formerly RUBEROID® SBS HeatWeld™ Plus

Description

RUBEROID® HW Plus Granule Membrane is a premium SBS modified bitumen membrane that can be installed without the use of hot asphalt. Its core is a strong, resilient non-woven polyester mat that is coated with a polymer-modified asphalt and surfaced with mineral granules.

Uses

RUBEROID® HW Plus Granule Membrane is designed for new roofing and re-covering applications as well as the construction of flashings. RUBEROID HW Plus Granule Membrane is also an ideal product for repairs of built-up roofing membranes or other modified bitumen systems.

Advantages

- System guarantees are available for up to 20 years.*
- Light weight—Installed roof designs weigh less than 2 pounds per square foot (9.8 kg/m²).
- Durable—Specially formulated modified asphalt gives RUBEROID® HW Plus Granule Membrane lasting performance.
- Specially formulated poly burn-off film allows for easy installation.

* See applicable guarantee for complete coverage and restrictions.

Advantages (Continued)

- Heat welding allows for kettle-free operation.
- Resilient—RUBEROID® HW Plus Granule Membrane's premium polyester mat core allows it to resist splits and tears due to its pliability and elongation characteristics.
- RUBEROID® HW Plus Granule Membrane is manufactured by GAF, a company with over 125 years in the roofing business.
- Available with black or white granules.



Applicable Standards

Meets ASTM D6164, Types I & II, Grade G
FM Approved
ICC ESR-1274
Miami-Dade County Product Control Approved
State of Florida Approved
UL/ULC Listed

Product Specifications (nominal)

Roll Size	1 square (107.7 gross sq. ft.) (10.0 m ²)
Roll Length	32.6' (9.9 m)
Roll Width	39.625" (1.0 m)
Approx. Roll Weight	105 lb (47.6 kg)
Product Thickness	0.165" (4.2 mm)

This product meets or exceeds the following ASTM D6164, Types I & II, Grade G, minimum requirements:

Property	Test Method	Value
Tensile Strength @ 0°F (min), lbf/in	ASTM D5147	100
Elongation @ 0°F (min), %	ASTM D5147	20
Low Temperature Flexibility (max), °F	ASTM D5147	0
Tear Strength (min), lbf	ASTM D5147	70
Dimensional Stability, (max) %	ASTM D5147	1