

# HYDROSTOP® PREMIUMCOAT® QUICK SPEC

## WARRANTY/GUARANTEE EXTENSION/RENEWAL (HS-12)

**NOTE:** The following "Quick Spec" is an abbreviated specification and is not meant to replace the detailed specification. Complete 3-part CSI System Specifications are available at [www.gaf.com](http://www.gaf.com).



### METHOD REQUIREMENTS

#### Required:

- The existing HydroStop® Roofing System must be inspected by GAF's Field Services to determine eligibility for recoat.
- Roof must be clean, dry, and tight.
- Adhesion test required.
- Apply at 50°F (10°C) and rising with no rain, dew, fog or freezing temperatures in the forecast for 24 hours.

#### Recommendations:

- GAF recommends that the surface temperature be at or less than 110°F (43°C) during application.

#### Installation Overview:

1. Roof must be inspected by GAF Field Services before work begins. Any issues found during the inspection must be repaired prior to the application.
2. Before coating is applied, an adhesion test is required to ensure an adhesion minimum of 2.0 pounds per linear inch (PLI). Test patches to be applied with rates listed below.
3. Power wash substrate to remove contaminants that could negatively affect adhesion.
4. Apply coating per the chart below.

CLEAN/ PRIME		
	Product	Rate (Gal/Sq)
Cleaner	UCC Cleaner ( <i>diluted</i> )	0.5 - 0.7
Primer	Not required	N/A

SEAMS & DETAILS <sup>1</sup>			
Treatment Type	Product	Total (Gal/Sq)	DFT* (mils)
3-Coursed Rates	HydroStop® Butter Grade and Fabric	4.0	43
Flashing Grade Only Rates	HydroStop® Butter Grade	2.0	19

Note: For other product options, please refer to our Seam Treatment Guide.

WARRANTY/GUARANTEE EXTENSION/RENEWAL						
	Finish Coat				Warranties/Guarantees Available	
	1st Coat (Gal/Sq) <sup>1</sup>	2nd Coat (Gal/Sq)	Total (Gal/Sq)	DFT* (mils)	Emerald Pledge™	Diamond Pledge™
10 Year	.75	.75	1.50	13	Yes	Yes
15 Year	1.00	1.00	2.00	17	Yes	Yes

\* Dry Film Thickness (DFT) is rounded to nearest mil, and is theoretical. Actual DFT will vary dependent on substrate profile, application technique and waste factor. Note: DFT for 3-coursed rates includes 6 mils for the fabric.

<sup>1</sup>Flashing rates are based on a 6" (152 mm) width.